

CLAIMS

1. An organic EL device comprising 1) a laminate consisting of an opposed pair of electrodes and an organic light-emitting layer sandwiched between the electrode, 2) a gas-tight housing accommodating said laminate and shielding off the external atmosphere and 3) a desiccating means disposed in isolation from said laminate within said gas-tight housing, characterized in that a preformed moisture-absorbing body as said desiccating means is fixedly secured to at least one part of said gas-tight housing.

2. An organic EL device according to Claim 1 wherein said preformed moisture-absorbing body comprises a desiccant and a resin component.

3. An organic EL device according to Claim 1 wherein said moisture-absorbing body is a body obtained by forming a mixture consisting of a desiccant and a resin component.

4. An organic EL device according to Claim 2 or 3 wherein the desiccant comprises at least one member selected from the group consisting of alkaline earth metal oxides and sulfate salts.

T08T07 25045860

5. An organic EL device according to Claim 2 or 3 wherein said resin component is at least one kind of gas-permeable resin.

6. A method of manufacturing an organic EL device comprising 1) a laminate consisting of an opposed pair of electrodes and an organic light-emitting layer sandwiched between the electrodes, 2) a gas-tight housing accommodating said laminate and shielding off the external atmosphere and 3) a desiccating means disposed in isolation from said laminate within said gas-tight housing, characterized in that the method includes a step of fixing said preformed moisture-absorbing body as desiccating means to at least one part of said gas-tight housing.

7. A method of manufacturing an organic EL device comprising 1) a laminate consisting of an opposed pair of electrodes and an organic light-emitting layer sandwiched between the electrodes, 2) a gas-tight housing accommodating said laminate and shielding off the external atmosphere and 3) a desiccating means disposed in isolation from said laminate within said gas-tight housing, characterized in that the method includes a first step comprising preparing a preformed moisture-absorbing body comprising a desiccant and a resin component and a second

0954067-10304
T08T01 2904860

step comprising fixing said preformed moisture-absorbing body as desiccating means to at least one part of said gas-tight housing.

8. A manufacturing method according to Claim 7 wherein said first step comprises forming a mixture consisting of a desiccant and a resin component to provide said preformed moisture-absorbing body.

0984037 104804
PATENT 29045860